

**AMENDMENTS TO THE CLAIMS**

This Listing of Claims will replace all prior versions and listings of claims in this application.

## Listing of Claims:

1. (Currently Amended) A layer (2''') arranged on an implant (1'') for bone or tissue structure (5), that constitutes a boundary or barrier for the purpose of increasing retention and has a thickness (T'), said layer (2''') further comprising:
  - a channel network (6) that gives the layer porosity,
  - wherein the channel network (6) has mouths (3', 4') on a surface (2a') of the layer (2''') adjacent to the bone or tissue structure and whose respective cross-sectional diameters (D) are in the range of 0.1  $\mu\text{m}$  to 10  $\mu\text{m}$  at the surface (2a') of the layer,
  - wherein ~~different sizes in the range of 0.1  $\mu\text{m}$  to 10  $\mu\text{m}$~~  for the cross-sectional diameters of the mouths -create conditions for bone growth,
  - wherein the mouths of the channel network have cross-sectional diameters that are less than the respective depths of the channels in and down into the layer as seen from said surface (2a'),
  - wherein the diameters of the mouths and the depths of the channels stimulate bone growth and contribute to the incorporation of the implant in the bone or tissue structure,
  - wherein the channel network (6) comprises a combination of contiguous channel branches (12, 13, 14, 15, 16) which extend in at least both vertical and lateral directions within the layer (2''') and toward a transition (11) between the layer (2''') and the implant (1''), and
  - wherein the layer has an average thickness in the range of 0.5 – 20  $\mu\text{m}$  and the layer is an oxide layer.
2. (Cancelled)

3. (Previously Presented) The layer according to claim 1, wherein the channel network (6) has channel branches (10) which extend in directions which are different than a depth direction of the layer or a radial direction of the implant.
4. (Cancelled)
5. (Previously Presented) The layer according to claim 1, wherein the layer has a thickness (T) which give a corrosion resistance for the implant as a whole.
6. (Previously presented) The layer according to claim 1, wherein the channel network (6) is arranged with a mouth arrangement (4') towards the bone or tissue structure (5), permitting increased bone growth penetration into the channel at said mouths.
7. (Cancelled)
8. (Cancelled)
9. (Previously Presented) The layer according to claim 1, wherein the layer has a high degree of porosity, with a number  $1 \times 10^7 - 1 \times 10^{10}$  pores/cm<sup>3</sup>.
10. (Previously Presented) The layer according to claim 1, wherein the surface has pores or channel mouth areas with the total channel network or pore volume lies in a range of  $5 \times 10^{-2}$  and  $10^{-5}$  cm<sup>3</sup>.
11. (Previously Presented) The layer according to claim 1, wherein the layer consists of or comprises a titanium oxide layer.
12. (Previously Presented) The layer according to claim 1, wherein the implant consists of a screw implant for application in a jaw bone.
13. (Previously Presented) The layer according to claim 1, wherein the layer forms a depot for applied bone-growth-initiating or bone-growth-stimulating agent or substance (17).

14. (Previously Presented) The layer according to claim 1, wherein an agent or substance migrates from a depot to the bone or tissue structure (5) by means of concentration diffusion.

15. (Currently Amended) An implant (1) for bone or tissue structure (5) comprising:  
a plurality of one or more layers (2) which constitute a boundary (or boundaries) for the purpose of increasing retention and each layer has a thickness, each layer further comprising:  
a channel network (6) which give the layer (2) porosity,  
wherein the ~~one or more~~plurality of layers are established on an undulating or uneven surface present on the implant and having a roughness value in the range of 0.4 - 5  $\mu\text{m}$ ,  
wherein the channel network (6) has mouths (3', 4') on a surface (2a') of the layer (2''') adjacent to the bone or tissue structure and whose respective cross-sectional diameters (D) are in the range of 0.1  $\mu\text{m}$  to 10  $\mu\text{m}$  at a surface of the layer,  
wherein different sizes in the range of 0.1  $\mu\text{m}$  to 10  $\mu\text{m}$  for the cross-sectional diameters of the mouths create conditions for bone growth,  
wherein the mouths of the channel network have cross-sectional diameters that are less than the respective depths (H) of the channels in and down into the layer as seen from said surface (2a'),  
wherein the diameters of the mouths and the extents of the channels stimulate bone growth and contribute to the incorporation of the implant in the bone or tissue structure, and  
wherein the channel network (6) comprises a combination of contiguous channel branches (12, 13, 14, 15, 16) which extend in at least both vertical and lateral directions within the layer (2''') and toward a transition (11) between the layer (2''') and the implant (1'') and,  
wherein the layer has an average thickness in the range of 0.5 – 20  $\mu\text{m}$  and the layer is an oxide layer.

16. (Withdrawn) Method for producing, by anodic oxidation, on an implant comprising or consisting of titanium, relatively thick oxide layers (2) on one or more titanium surfaces which are intended to be placed against or arranged next to one or more tissue and/or bone growth areas (5), where at least the part or parts supporting the said surface or surfaces are prepared and immersed in electrolyte (26) and the implant is brought into contact with an electrical energy

source above the electrolyte surface and the oxidation process is established by also connected to the energy source a counter-electrode arranged in the electrolyte (26), characterized in that diluted organic acids and/or small quantities of hydrofluoric acids or hydrogen peroxide are added to the electrolytic composition, and in that the energy source is chosen to operate with voltage values of at least 150 volts, for example with voltage values in the range of 200 – 400 volts.

17. (Withdrawn) Method according to Patent Claim 12, characterized in that the voltage (28) is varied at times for the same implant in order to create different channel or pore sizes within the same surface area.

18. (Withdrawn) Method according to Patent Claim 16, characterized in that the position of the implant in the electrolyte is changed together with the composition of the electrolyte (26) and/or the voltage (28) in order to create different oxide thicknesses (T, T') and/or areas of different porosity or pore or channel characteristics.

19.-21. (Cancelled)

22. (Currently Amended) The layer~~method~~ of claim 1, wherein the implant has a surface further comprising mouths, channels and channel branches having diameters in a range of 0.1  $\mu\text{m}$  to 1.5  $\mu\text{m}$  and that comprise 20% of the surface.

23. (Currently Amended) The implant~~method~~ of claim 15, wherein the implant has a surface further comprising mouths, channels and channel branches having diameters in a range of 0.1  $\mu\text{m}$  to 1.5  $\mu\text{m}$  and that comprise 20% of the surface.